

# InsoLion® GRE



## Description

The InsoLion® GRE gasket consists of a G10 glass reinforced (GRE) carrier with 2 modified PTFE sealing faces.

Proprietary machining of the carrier allows correct location of the sealing faces, with the depth / profile designed to achieve correct compression and groove fill.

## Application Guidelines

- Flange insulation and electrical isolation in conjunction with cathodic protection
- Specified for plant wide use on the majority of flange specifications including ASME, API, EN, BS and DIN.
- Insulation between dissimilar metals to prevent galvanic corrosion

**Maximum temperature** +120°C (248°F)

**Minimum temperature** -128°C (-200°F)

**Max pressure** 51.7Bar (750psi)  
ASME Class 300, PN40

## Availability

InsoLion® GRE can be supplied in sizes from ½" to 24" diameter to match the majority of flange specifications including ASME, API, EN, BS, ISO and DIN

Nominal thickness of InsoLion GRE is 3.2mm

Custom dimensions and sizing options are available upon request.

InsoLion GRE is supplied as a kit suitable for the specific flange size and class rating required.

This kit includes:

1. InsoLion GRE gasket
2. G10 bolt sleeves
3. G10 Washers
4. Metallic backup washers in Zinc plated carbon steel or stainless steel

## Typical physical properties

### GRE Laminate

GRE material is Type-approved to NEMA LI-1 G10 standards, and conform to BS EN 60893-3-2-EPGC201.

Property	Test Method	Parameters	Typical Physical Property
Water Absorption	ISO 62	mg	Maximum 22.0
Electric Strength	IEC 60243-1	kV/mm	Minimum 15
Breakdown Voltage	IEC 60243-1	kV	Minimum 80
Insulation Resistance	IEC 60167	MΩ	Minimum 5.0 x 10 <sup>4</sup>

Compressive Strength	ASTM D 695	MPa	Minimum 345
Impact Strength	ASTM D 229	ft.lb/in	Minimum 12.0
Tensile Strength	ASTM D 638	MPa	Minimum 345
Shear Strength	ASTM D 732	MPa	Minimum 152

## Information

**Health warning:** If PTFE products are heated to elevated temperatures, fumes will be produced which may give unpleasant effects, if inhaled. Whilst some fumes are emitted below 300°C (572°F) from PTFE, the effect at these temperatures is negligible. Care should be taken to avoid contaminating tobacco with particles of PTFE or PTFE dispersion, which may remain on hands or clothing. Safety Data Sheets (SDS) are available on request.

Information given in this publication is given in good faith and represents the results of specific individual tests performed in a laboratory by James Walker or third parties in accordance with the methodologies described in this publication. No representation or warranty is given in relation to such information. Values and/or operating limits given in this publication are not an indication that these values and/or operating limits can be applied simultaneously. While such results may comprise useful additional information and are industry standard tests, they are no substitute for conducting your own tests and engineering analysis and satisfying yourself as to the suitability of the material or product you select. Please also note that a material or product tested in accordance with the quoted methodology may not perform to such values in application and/or under different test conditions or methodologies for a variety of reasons. These include, but are not limited to the environment to which it is exposed, storage, handling and installation processes, interactions with housings and other parts or, in the case of materials, the design of any product made from that material. Our personnel will be happy to discuss any historical examples we have of the material or product having been previously used in a particular application.

To ensure you are working with the very latest product specifications, please consult the relevant section of the James Walker website: [www.jameswalker.biz](http://www.jameswalker.biz).

**[www.jameswalker.biz](http://www.jameswalker.biz)**